

NONWOVEN GEOTEXTILES

Protect your geomembrane materials from damage while staying compliant with your industry regulations. These nonwoven geotextiles are an industry favorite due to their cost-effective properties and consistent filtration.

Manufactured from high-quality polypropylene fibers, Layfield's nonwoven geotextiles achieve their unique properties through the interlocking fibers that are formed during the needle-punching process. They are commonly used to provide filtration; separation; protection; and drainage.

April 2023		Non-Woven Geotextiles (US Values)									
Material Properties		ASTM	LP3.5	LP4	LP4.5	LP6	LP7	LP8	LP10	LP12	LP16
	Grab Tensile (lbs)	D4632	90	100	120	160	180	205	250	300	380
	Elongation (%)	D4632	50	50	50	50	50	50	50	50	50
	Tear (lbs)	D4533	40	45	50	60	75	80	100	115	140
	CBR Punc (lbs)	D6241	250	250	310	410	450	500	700	800	1025
	AOS (sieve)	D4751	50	70	70	70	70	80	100	100	100
	Permittivity (sec-1)	D4491	2.0	2.0	1.7	1.5	1.4	1.4	0.83	0.83	0.7
	Water Flow (gpm/ft2)	D4491	145	140	120	110	100	95	75	65	50
	UV (500 hrs)	D4355	70%	70%	70%	70%	70%	70%	70%	70%	70%
	Roll Size (ft)		15 x 360	15 x 360	15 x 360	15 x 3002	15 x 3002	15 x 3002	15 x 300	15 x 300	15 x 150
Roll Weight ^{1,4} (kg)		160	167	190	202	220	250	308	400	250	

Note1: Typical values. All other values are minimum average roll values (MARV).

Note2: LP6, LP7, and LP8 may be 15 x 360 ft depending on inventory.

Note3: LP10 also available in 1.2 and LP12 in 1.0

Note4: This is average shipping roll weight - it's not to be used to calculate grams/m² weight of the actual material.

Disclaimer: Layfield disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

For up-to-date technical information, be sure to visit us online at www.LayfieldGroup.com

NONWOVEN GEOTEXTILES

April 2023

Non-Woven Geotextiles (Metric Values)

Material Properties		ASTM	LP3.5	LP4	LP4.5	LP6	LP7	LP8	LP10	LP12	LP16
	Grab Tensile (N)	D4632	401	445	533	711	800	911	1,112	1,330	1,690
	Elongation (%)	D4632	50	50	50	50	50	50	50	50	50
	Tear (N)	D4533	178	200	222	267	333	356	444	511	623
	CBR Punc (N)	D6241	1110	1110	1380	1820	2000	2220	3114	3510	4560
	AOS (microns)	D4751	250	212	212	212	212	180	150	150	150
	Permittivity (sec-1)	D4491	2.0	2.0	1.7	1.5	1.4	1.4	0.83	0.83	0.7
	Water Flow (l/min/m2)	D4491	5,900	5,689	4,885	4,480	4,074	3,870	3,056	2,650	2,035
	UV (500 hrs)	D4355	70%	70%	70%	70%	70%	70%	70%	70%	70%
	Roll Size (m)		4.57 x 110	4.57 x 110	4.57 x 110	4.57 x 91.4	4.57 x 91.4	4.57 x 91.4	4.57 x 91.4	4.57 x 91.4	4.57 x 45.7
	Roll Weight ^{1,4} (kg)		73	78	86	92	99	113	140	181	112

Disclaimer: Layfield disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

For up-to-date technical information, be sure to visit us online at www.LayfieldGroup.com

NONWOVEN GEOTEXTILES

For up-to-date technical information, be sure to visit us online at www.LayfieldGroup.com