

# HYDRANET® HP GEONET

Layfield's HydraNet® HP is a high-performance geonet designed to enhance containment system resilience. Manufactured with next generation resins, it delivers superior durability and long-term performance. Available in multiple thicknesses, it can be laminated to nonwoven geotextiles or paired with Geovolt® for electric leak detection. HydraNet® HP offers exceptional resistance to heat, chemicals, and UV, making it ideal for challenging applications.

July 2025

## HydraNet® HP GeoNet

Property	Test Method	Unit	Value
Thickness, MAV	ASTM D 5199	mils (mm)	315 (8.00)
Density, MAV	ASTM D 792	g/cm <sup>3</sup>	0.94
Tensile strength (MD), MAV	ASTM D 7179	lbs/in (kN/m)	88 (15.4)
Carbon Black Content, MAV	ASTM D 4218	%	2
Melt Flow Index <sup>(1)</sup> , MaxAV	ASTM D 1238	g/10 min	1.0
Flow Rate/Width <sup>(2)</sup> , MAV	ASTM D 4716	gal/min/ft (l/min/m)	3.8 (48)
Transmissivity <sup>(2)</sup>	ASTM D 4716	gal/min/ft (m <sup>2</sup> /s)	38 (8x10 <sup>-3</sup> )
ESCR <sup>(3)</sup> , Typical	ASTM D 1693	Hours	>5,000
Oxidative Induction Time, min	ASTM D 3895	minutes	40

### Notes:

(1) Test conditions 190°C /2.16 kg, tested on the resin.

(2) Measured using water at 21±2 °C (70 ± 4 °F) with gradient of 0.1 and confining pressure of 10,000 psf (480 kPa) between steel plates after 15 minutes seating time. Values may vary with individual labs.

(3) 122°F (50°C), 100% Igepal, F50.

**Disclaimer:** Layfield disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

For up-to-date technical information, be sure to visit us online at [www.LayfieldGroup.com](http://www.LayfieldGroup.com)